

LASTOFLEX-TR

One component, crystal clear, solvent-based, liquid applied waterproofing membrane based on aliphatic PU resins.

PHYSICAL PROPERTIES

- Elastic performance and working deformability.
- Temperature variations resistance : -40 to 80 °C.
- Adhering ability.
- Excellent resistance to UV radiation and moisture exposure (**QUV-se ACCELERATED WEATHERING CYCLIC CORROSION TESTER**)
2000 h accelerated weathering, consisting of the following cycles:
 - a. 4h UV exposure, at 60°C
 - b. 4h moisture exposure, at 50°C.**Result:** LASTOFLEX-TR retains its mechanical properties and elastic performance. No yellowing observed.
- High resistance to water.
- Resistance to mechanical strain and friction.

TECHNICAL PROPERTIES

- | | |
|--|-------------------------|
| • Specific gravity : | 1,0 |
| • Surface membrane formation time (23 °C, 50% R.H.): | 90 min |
| • Elongation at break point (DIN 53504) : | 160% |
| • Tensile strength (DIN 53504) : | 10,50 N/mm ² |
| • Hardness SHORE A : | 75 |

APPLICATION FIELDS

LASTOFLEX-TR is suitable for all waterproofing applications where a transparent sealer is required. It is recommended for waterproofing tiles, natural stones, wood, concrete, glass, etc. ***It is especially suitable for waterproofing balconies and terraces.***

APPLICATION INSTRUCTIONS

Weathering conditions:

Rainy weather should be avoided.

Preparation:

The application surface must be dry and clean from loose particles, dust, etc.

Application:

LASTOFLEX-TR is applied by roll, brush or air-gun in 1-2 layers. Time interval between two layers is at least 3-4 h and not more than 48 h. However, this largely depends on environmental conditions.

On glazed tiles, **PRIMER DM** should always be used prior to the application of **LASTOFLEX-TR**.

Consumption:

The consumption largely depends on the roughness of the substrate. Typical total consumption in one or two layers is 0.2 – 1.0 Kg/m².

Curing time:

12 to 24 h, depending on environmental conditions.

Packaging:

Lids of 1 kg, 5 kg, 20 kg.

Warning to users

The information contained in this document is given in good faith based on our current knowledge. It is only an indication and is in no way binding, particularly as regards infringement of or prejudice to third party rights through the use of our products. ELASTOTET GUARANTEES THAT ITS PRODUCTS COMPLY WITH ITS SALES SPECIFICATIONS. This information must on no account be used as a substitute for necessary prior tests which alone can ensure that a product is suitable for a given use. Users are responsible for ensuring compliance with local legislation and for obtaining the necessary certifications and authorisations. Users are requested to check that they are in possession of the latest version of this document and ELASTOTET is at their disposal to supply any additional information.